

Product Data sheet: PM-LL 22B02

Characteristic	Typical value	Unit	Test method
Melt flow index	1.8 - 2.2	g/10 min	ASTM D1238
Density	0,920-0,924	g/l	ASTM D1505
F/E Ratio	<30	—	ASTM D1238
Yellowness index	0,5	—	ASTM D1925
Ti content	2	Pgm wt	MTM 15636
Elmendorf Tear Strength, MD	35	gr/25µm	ASTM D1922
Film Elongation at Break, MD	780	%	ASTM D882
Film Tensile Strength at Break, MD	54	MPa	ASTM D882
Film Tensile Strength at Yield, MD	18	MPa	ASTM D882

Name: Linear Low Density Polyethylene

Chemical Formula: LLDPE 22B02

Grade: 22B02

Physical Characteristics: Transparent colorless granules

Suppliers: Lorestan & Mahabad Petrochemical

Packaging: 25 kg Bags

 021-40660017-20

 Shad Abad Iron Market-Ava Jeneral Complex.No.1

 www.arkapolymer.ir
www.20polymer.ir