

MOPLen MR230C

Polypropylene

Property	Unit	Test method	Value
MFI (190°C, 5 kg)	g/10 min	R 1133	0.4 - 0.6
MFI (230°C, 2.16 kg)	g/10 min	R 1133	< 0.3
Hardness Rockwell	R scale	R20391	93
Thermal conductivity (23°C)	W/mK	R314	0.17
Specific gravity	----	R118	0.89
Flexural modulus	MPa	R1183	835
Tensile strength at yield	MPa	R 527	28
Elongation at break	%	R 527	>430
Vicat softening point (9.8N)	°C	R 306	135
HDT (0.45 MPa)	°C	R75	80
Accelerated aging at 135°C	hours	R457	>9,000

Product Description:

Polypropylene MR230C exhibits excellent heat resistance, and is designed to produce items with superior toughness, even at low temperature.

Application:

Polypropylene MR230C is well suited for production of pressure pipes for industry, heating pipes and under floor hot water heating, domestic service pipes (hot and cold water) and weldable fittings.

Marun petrochemical complex

 021-40660017-20

 Shad Abad Iron Market-Ava Jeneral Complex.No.1

 www.arkapolymer.ir
www.20polymer.ir