

## Jampilen EP548R

### HETEROPHASIC COPOLYMER

| Property                                 | Unit              | Test method | Value |
|--|-------------------|-------------|-------|
| MFI (230 oC, 2.16kg)                     | g/10min           | ASTM D1238  | 21    |
| Density                                  | g/cm <sup>3</sup> | ASTM D1505  | 0.9   |
| Flexural Modulus                         | MPa               | ASTM D790   | 1500  |
| Tensile Strength at Yield                | MPa               | ASTM D638   | 27    |
| Tensile Elongation at Yield              | %                 | ASTM D638   | 7     |
| Izod Impact Strength (notched) at 23 oC  | J/m               | ASTM D256   | 85    |
| Izod Impact Strength (notched) at -20 oC | J/m               | ASTM D256   | 50    |
| Rockwell Hardness                        | R Scale           | ASTM D785   | 98    |
| Vicat softening point (10N)              | oC                | ASTM D1525  | 149   |
| H.D.T. (0.46 Mpa)                        | oC                | ASTM D648   | 110   |
| Accelerated oven ageing in air at 150 oC | hours             | ASTM D3012  | 360   |

**Product description:** "Jampilen EP548R" is a nucleated, antistatic formulated, high fluidity heterophasic copolymer used for thin-walled injection molding. Items made with "Jampilen EP548R" exhibit high stiffness, relatively good impact resistance and excellent antistatic properties. Due to its excellent moldability and short cycle times, "Jampilen EP548R" allows high productivity rates. The finished items show good mechanical properties, and high dimensional stability.

Application: "Jampilen EP548R" is very well suited for the production of thin-walled articles or articles with long flow paths such as flower pots, containers, housewares, filters, filters housings and appliance components

JAM PETROCHEMICAL COMPANY

 021-40660017-20

 Shad Abad Iron Market-Ava Jeneral Complex.No.1

 [www.arkapolymer.ir](http://www.arkapolymer.ir)  
[www.20polymer.ir](http://www.20polymer.ir)