

EVA (VA800)

Ethylene Vinyl Acetate Copolymer

Properties	Nominal Value	Unit	Test Method
Melt Index	20	g/10min	ASTM D1238
Vinyl Acetate	28	wt. %	LC Method
Density	0.95	g/cm ³	ASTM D1505
Melting Point	69	°C	LC Method
Hardness	25	D scale	ASTM D2240
Vicat Softening Point	< 40	°C	ASTM D1525

Description:

SEETEC VA800 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC VA800 resin, with 28% VA content, is an excellent raw material in the application of hot melt adhesives.

Additives:

Antioxidant , Free flow agent

Applications: Hot melt adhesives

Producer: Honam.Korea.

ARKA
POLYMER