

## EVA (VA810)

Ethylene Vinyl Acetate Copolymer

Properties	Nominal Value	Unit	Test Method
Melt Index	45	g/10min	ASTM D1238
Vinyl Acetate	33	wt. %	LC Method
Density	0.957	g/cm <sup>3</sup>	ASTM D1505
Melting Point	62	°C	LC Method
Hardness	24	D scale	ASTM D2240
Vicat Softening Point	< 40	°C	ASTM D1525

### Description:

SEETEC VA810 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC VA810 resin, with 33% VA content, is an excellent raw material in the application of hot melt adhesives.

### Additives:

Antioxidant , Free flow agent.

### Applications:

Hot melt adhesives.

Producer: Honam.Korea.

**ARKA**  
POLYMER