

EVA (VA900)

Ethylene Vinyl Acetate Copolymer

Properties	Nominal Value	Unit	Test Method
Melt Index	150	g/10min	ASTM D1238
Vinyl Acetate	28	wt. %	LC Method
Density	0.95	g/cm ³	ASTM D1505
Melting Point	67	°C	LC Method
Hardness	21	D scale	ASTM D2240
Vicat Softening Point	< 40	°C	ASTM D1525

Description:

SEETEC VA900 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC VA900 resin, with 28% VA content, is an excellent raw material in the application of hot melt adhesives.

Additives:

Antioxidant , Free flow agent.

Applications:

Hot melt adhesives.

Producer: LOTTE.Korea.

ARKA
POLYMER