

## EVA (VA910)

Ethylene Vinyl Acetate Copolymer

Properties	Nominal Value	Unit	Test Method
Melt Index	400	g/10min	ASTM D1238
Vinyl Acetate	28	wt. %	LC Method
Density	0.95	g/cm <sup>3</sup>	ASTM D1505
Melting Point	65	°C	LC Method
Hardness	18	D scale	ASTM D2240
Vicat Softening Point	< 40	°C	ASTM D1525

### Description:

SEETEC VA910 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC VA910 resin, with 28% VA content, is an excellent raw material in the application of hot melt adhesives.

### Additives:

Antioxidant , Free flow agent.

### Applications:

Hot melt adhesives.

Producer: LOTTE.Korea.

**ARKA**  
POLYMER